

Technical Bulletin # 1033B

Bulletin Description

ITW QUICKSET is a two-component high strength, fast-setting, multi-purpose epoxy with a convenient mixing ratio of 1:1 by volume.

Use & Benefits

ITW QUICKSET can be used as a liquid shim, an anchoring adhesive or as a structural gap filler. It is recommended for applications requiring rapid turnaround of equipment but not for equipment requiring precise alignment (i.e. less than 0.005" or 0.127 mm movement over the life of the equipment).

ITW QUICKSET can be quickly mixed and applied under concrete blocks, between steel plates or between concrete and steel. ITW QUICKSET was designed to fill a void within 15 minutes then harden to 78 shore D in 30 minutes and 84 Shore D in 4 hours at a concrete / steel temperature of 70° F (21° C). ITW QUICKSET will reach a minimum compressive strength of 14,500 psi (101.5 MPa) in about 6 hours at 70° F (21° C).

Design Considerations

Because ITW QUICKSET was designed to be installed within 15 minutes after mixing, the void area it fills must be of a size that can be completely filled within that time based on the application method chosen. ITW QUICKSET is a hot curing epoxy so the temperature of the epoxy, the temperature of the concrete or steel and the ambient temperature must be taken into consideration when installing it. A maximum thickness of 18mm (3/4 inch) recommended at 21° C (70° F) but ITW QUICKSET can be applied at ambient temperatures between 40° F and 85° F (5° C and 29° C). For applications outside either of these ranges contact the Engineering Services Department at ITW Polymer Technologies.



Application Instructions

ITW QUICKSET comes in gallon cans, 5 gallon buckets or 55 gallon drums. It can be mixed and applied by either mixing it with a Jiffy Mixing blade for 3 minutes then pouring it in place or by using a manual or automated mixing and dispensing system.

An automated mixing and dispensing system is recommended when it is necessary to apply a large volume of the epoxy in a short period of time. An automated dispensing system consists of metering pumps, hoses and a manually operated dispensing gun with a static mixing nozzle.

Depending on the temperature of the concrete or steel, the thickness of the gap to be filled and the importance of a fast cure rate, ITW QUICKSET epoxy resin and hardener may need to be individually pre-mixed prior to dispensing. It should also be preconditioned for 24 hours while still in the drum to 65°F to 75°F (18°C to 24°C) prior to dispensing.

Please consult ITW Polymer Technologies for additional information.



ITW POLYMER TECHNOLOGIES

130 Commerce Drive • Montgomeryville, PA 18936

Phone 215-855-8450 • Fax 215-855-4688 • www.chockfastgrout.com



Physical Properties

COMPRESSIVE STRENGTH:	14,500 psi (101.49 MPa)	ASTM D-695
COMPRESSIVE MODULUS OF ELASTICITY:	347,000 psi (2392.5 MPa)	ASTM D-695
LINEAR SHRINKAGE:	< 0.5%	ASTM D-2566
FLEXURAL STRENGTH:	15,400 psi (106.18 MPa)	ASTM C-580
FLEXURAL MODULUS OF ELASTICITY:	191,000 psi (1316.9 MPa)	ASTM D-580
TENSILE STRENGTH:	8,800 psi (60.67 MPa)	ASTM D-638
TENSILE MODULUS:	191,000 psi (1316.9 MPa)	ASTM D-638
TENSILE LAP SHEAR STRENGTH:	908 psi (6.26 MPa) after 30 min.	ASTM D-1002
	>1,300 psi (9 MPa) after 7 days	
% ELONGATION AT BREAK:	5.9%	ASTM D-638
SPECIFIC GRAVITY OF RESIN:	1.17	
VISCOSITY OF RESIN:	48,800 cps @ 10 RPM using Viscosity Brookfield Viscometer Spindle #3	
SPECIFIC GRAVITY OF HARDENER:	1.66	
VISCOSITY OF HARDENER:	8,800 cps @ 20 RPM using Viscosity Brookfield Viscometer Spindle #3	
MIXED VISCOSITY:	27,000 cps @ 20 RPM using Viscosity Brookfield Viscometer Spindle #3	
GEL TIME @ 75° F (24°C):	15 min 100 gram mass	
SHORE D HARDNESS:	70 @ 30 Minutes @ 70oF	
	78 @ 1 Hour	
	82 @ 4 Hours	
	84 @ 1 Day	
FIRE RESISTANCE:	Self Extinguishing	ASTM D 635

Product Information

UNIT COVERAGE:	2 gal Unit: 435 in. ³ (7.1 L) 10 gal Unit: 2,282 in. ³ (37.4 L) 110 gal unit: 21,131 in. ³ (346.3 L)
APPLICATION TEMPERATURE:	41°F (5°C) to 95°F (35°C)
PACKAGING per Unit:	2 gal Unit: Resin – 9.3 lbs. (4.2 kg), Hardener – 12.86 lbs. (5.8 kg) in two (2) 1 gal cans 10 gal Unit: Resin – 48.5 lbs. (22 kg), Hardener – 68 lbs. (30.8 kg)) in two (2) 5 gal cans 110 gal unit: Resin – 441 lbs. (200 kg), Hardener – 641 lbs. (291 kg) in two (2) 55 gal drums
CURE TIME (approximate):	6 hours @ 21° C (70° F)
POT LIFE:	15 min. @ 21° C (70° F)
SHELF LIFE:	2 years
CLEAN UP:	IXT-59 or similar epoxy solvent

Date 01/2012

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support.

Warranty: ITW Polymer Technologies, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment.

Warranty Claims: If any product fails to meet the above, ITW Philadelphia Resins will, at its option, either replace the product or refund the purchase price. ITW Polymer Technologies will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered.

Disclaimer: ITW Polymer Technologies makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose.

Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Polymer Technologies' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Polymer Technologies' election. Under no circumstances shall ITW Polymer Technologies be liable for any indirect, incidental or consequential damages.

Modification of Warranty: No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Polymer Technologies. No term of any purchase order shall serve to modify any provision of this document.

Mediation and Arbitration: If any dispute arises relating to products or product warranties, either the purchaser or ITW Polymer Technologies may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.